



SZABO SCANDIC

Part of Europa Biosite

Produktinformation



Forschungsprodukte & Biochemikalien



Zellkultur & Verbrauchsmaterial



Diagnostik & molekulare Diagnostik



Laborgeräte & Service

Weitere Information auf den folgenden Seiten!
See the following pages for more information!



Lieferung & Zahlungsart

siehe unsere [Liefer- und Versandbedingungen](#)

Zuschläge

- Mindermengenzuschlag
- Trockeneiszuschlag
- Gefahrgutzuschlag
- Expressversand

SZABO-SCANDIC HandelsgmbH

Quellenstraße 110, A-1100 Wien

T. +43(0)1 489 3961-0

F. +43(0)1 489 3961-7

mail@szabo-scandic.com

www.szabo-scandic.com

[linkedin.com/company/szaboscandic](https://www.linkedin.com/company/szaboscandic) 

PA1

PeptiGel® Alpha 1

Description

PeptiGel® Alpha 1 is a ready-to-use fully synthetic neutrally charged peptide hydrogel. PeptiGel® Alpha 1 is biologically relevant, mimics the extracellular matrix and is suitable for the culture of a variety of cells, including chondrocytes, nucleus pulposus cells and suspension cells.

PeptiGel® Alpha 1 is a stiffer hydrogel when compared to Alpha 4 but has consistent mechanical stiffness (G') and pore size, resulting in excellent reproducible results. PeptiGel® Alpha 1 can be used for both *in-vitro* and *in-vivo* applications with physiologically and clinically relevant results.

Specifications

Charge	Neutral
Mechanical Properties (kPa)	3.0 – 5.0
GFOGER from Collagen	No
RGD from Fibronectin	No

Stability and Storage

Stability and Storage At least 6 months shelf life when stored at 4°C as supplied

General Guidance for Handling and Use of PeptiGels®

- **Pipetting:** It is recommended to use a positive displacement pipette (e.g. Gilson piston pipette) to facilitate accurate PeptiGel® handling and for mixing PeptiGel® for 3D cell culture.
- **Air bubbles:** Prior to starting work with PeptiGel®, any visible air bubbles can be removed by one or more rounds of centrifugation (1,600 x g for 1 minute at room temperature). When mixing PeptiGel® for 3D cell culture, the formation of air bubbles should be minimised. This can be achieved by making sure cells are released slowly into the hydrogel whilst gradually bringing the pipette upwards, in a stirring motion. In addition, make sure the pipette tip never leaves the hydrogel while mixing.
- **Diluting:** PeptiGels® can be diluted with HPLC water to help you achieve your desired mechanical strength/s. PeptiGels® are also supplied with a range of mechanical strengths.

Resources and Protocols

For additional resources and specific protocols, [click here](#) or scan the QR code.

