



SZABO SCANDIC

Part of Europa Biosite

Produktinformation



Forschungsprodukte & Biochemikalien



Zellkultur & Verbrauchsmaterial



Diagnostik & molekulare Diagnostik



Laborgeräte & Service

Weitere Information auf den folgenden Seiten!
See the following pages for more information!



Lieferung & Zahlungsart

siehe unsere [Liefer- und Versandbedingungen](#)

Zuschläge

- Mindermengenzuschlag
- Trockeneiszuschlag
- Gefahrgutzuschlag
- Expressversand

SZABO-SCANDIC HandelsgmbH

Quellenstraße 110, A-1100 Wien

T. +43(0)1 489 3961-0

F. +43(0)1 489 3961-7

mail@szabo-scandic.com

www.szabo-scandic.com

[linkedin.com/company/szaboscandic](https://www.linkedin.com/company/szaboscandic)

**Corning Incorporated
Life Sciences**

Registered
ISO 9001:2008

Product Description

Catalog Number: 3883

Product Description: Corning® 96-well half area, non-treated, white plate with clear flat bottom, without lid

Component Materials:

- Plate walls - Virgin Polystyrene, meets *USP, Class VI* requirements for plastic containers and closures. White concentrate
- Plate bottom - Virgin Polystyrene, meets *USP, Class VI* requirements for plastic containers and closures.

Product Dimensions:

- | | | | | | |
|--------------------------|---|--------------|---------------------------|---|----------|
| Length of Plate | - | 5.030 in. | Diameter of Well @ top | - | .197 in. |
| Width of Plate | - | 3.365 in. | Diameter of Well @ bottom | - | .177 in. |
| Depth of Well | - | .452 in. | Height without Lid | - | .560 in. |
| Tolerances of Dimensions | - | +/- .010 in. | Volume per Well | - | 200 µl |

Surface Characterization:

Surface is characterized to be medium binding.

Binding Characteristics:

Each lot has been tested for the attribute of well to well protein binding utilizing a luminescent immunoassay to measure precision. Coefficient of variation must be $\leq 8\%$.

Optical Characteristics:

The product is made of opaque white polystyrene walls to minimize well to well crosstalk and background fluorescence and /or luminescence. The bottom is made of clear polystyrene to allow visual clarity for optical density or bottom read fluorescent / luminescent measurements.

Performance Testing:

Each manufacturing lot is sampled and tested in accordance with Standard Operating Procedures.

- | | |
|--------------------|--|
| Visual Attributes: | Visual and microscopic examination of the product. |
| Packaging: | Inspection for accurate labeling, and correct product configuration. |
| Functional: | Luminescent immunoassay |

Lot Number Designation:

8 Digit Lot Number: First 3 digits - Julian Date, start of manufacturing; Next 2 digits - Year of manufacture; Last 3 digits - Batch identification.

Rev No: 1