



# SZABO SCANDIC

Part of Europa Biosite

## Produktinformation



Forschungsprodukte & Biochemikalien



Zellkultur & Verbrauchsmaterial



Diagnostik & molekulare Diagnostik



Laborgeräte & Service

Weitere Information auf den folgenden Seiten!  
See the following pages for more information!



### Lieferung & Zahlungsart

siehe unsere [Liefer- und Versandbedingungen](#)

### Zuschläge

- Mindermengenzuschlag
- Trockeneiszuschlag
- Gefahrgutzuschlag
- Expressversand

### SZABO-SCANDIC HandelsgmbH

Quellenstraße 110, A-1100 Wien

T. +43(0)1 489 3961-0

F. +43(0)1 489 3961-7

[mail@szabo-scandic.com](mailto:mail@szabo-scandic.com)

[www.szabo-scandic.com](http://www.szabo-scandic.com)

[linkedin.com/company/szaboscandic](https://www.linkedin.com/company/szaboscandic) 

# Amberlite® IRA-900

sc-291888



Material Safety Data Sheet

Hazard Alert Code Key: **EXTREME** **HIGH** **MODERATE** **LOW**

## Section 1 - CHEMICAL PRODUCT AND COMPANY IDENTIFICATION

### PRODUCT NAME

Amberlite® IRA-900

### STATEMENT OF HAZARDOUS NATURE

Not considered a hazardous substance according to OSHA 29 CFR 1910.1200.

### NFPA



### SUPPLIER

Santa Cruz Biotechnology, Inc.  
2145 Delaware Avenue  
Santa Cruz, California 95060  
800.457.3801 or 831.457.3800

### EMERGENCY:

ChemWatch  
Within the US & Canada: 877-715-9305  
Outside the US & Canada: +800 2436 2255  
(1-800-CHEMCALL) or call +613 9573 3112

### SYNONYMS

"chromatographic media"

## Section 2 - HAZARDS IDENTIFICATION

### CHEMWATCH HAZARD RATINGS

	Min	Max
Flammability:	1	
Toxicity:	0	
Body Contact:	0	Min/Nil=0 Low=1
Reactivity:	1	Moderate=2 High=3
Chronic:	0	Extreme=4

### CANADIAN WHMIS SYMBOLS

None

## EMERGENCY OVERVIEW

### RISK

### POTENTIAL HEALTH EFFECTS

#### ACUTE HEALTH EFFECTS

##### SWALLOWED

- The material has NOT been classified as "harmful by ingestion". This is because of the lack of corroborating animal or human evidence.

##### EYE

- Although the material is not thought to be an irritant, direct contact with the eye may cause transient discomfort characterized by tearing or conjunctival redness (as with windburn). Slight abrasive damage may also result.

##### SKIN

- The material is not thought to produce adverse health effects or skin irritation following contact (as classified using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable gloves be used in an occupational setting.

##### INHALED

- The material is not thought to produce adverse health effects or irritation of the respiratory tract (as classified using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable control measures be used in an occupational setting.
- Persons with impaired respiratory function, airway diseases and conditions such as emphysema or chronic bronchitis, may incur further disability if excessive concentrations of particulate are inhaled.

#### CHRONIC HEALTH EFFECTS

- Long-term exposure to the product is not thought to produce chronic effects adverse to the health (as classified using animal models); nevertheless exposure by all routes should be minimized as a matter of course. Long term exposure to high dust concentrations may cause changes in lung function i.e. pneumoconiosis; caused by particles less than 0.5 micron penetrating and remaining in the lung.

## Section 3 - COMPOSITION / INFORMATION ON INGREDIENTS

NAME	CAS RN	%
Amberlite IRA-900 Ion Exchange Resin	9050-97-9	>98

## Section 4 - FIRST AID MEASURES

##### SWALLOWED

· Immediately give a glass of water. · First aid is not generally required. If in doubt, contact a Poisons Information Center or a doctor.

##### EYE

- If this product comes in contact with eyes: · Wash out immediately with water. · If irritation continues, seek medical attention.

##### SKIN

- If skin or hair contact occurs: · Flush skin and hair with running water (and soap if available). · Seek medical attention in event of irritation.

##### INHALED

· If dust is inhaled, remove from contaminated area. · Encourage patient to blow nose to ensure clear passage of breathing. · If irritation or discomfort persists seek medical attention.

#### NOTES TO PHYSICIAN

- Treat symptomatically.

## Section 5 - FIRE FIGHTING MEASURES

Vapor Pressure (mmHg):	16.951 @20C(H2O)
Upper Explosive Limit (%):	Not available
Specific Gravity (water=1):	1.1-1.4
Lower Explosive Limit (%):	Not available

#### EXTINGUISHING MEDIA

· Foam.  
· Dry chemical powder.

## FIRE FIGHTING

- Alert Emergency Responders and tell them location and nature of hazard.
- Wear breathing apparatus plus protective gloves.

## GENERAL FIRE HAZARDS/HAZARDOUS COMBUSTIBLE PRODUCTS

- Combustible solid which burns but propagates flame with difficulty.
- Avoid generating dust, particularly clouds of dust in a confined or unventilated space as dusts may form an explosive mixture with air, and any source of ignition, i.e. flame or spark, will cause fire or explosion. Dust clouds generated by the fine grinding of the solid are a particular hazard; accumulations of fine dust may burn rapidly and fiercely if ignited.

Combustion products include: carbon monoxide (CO), carbon dioxide (CO<sub>2</sub>), sulfur oxides (SO<sub>x</sub>), other pyrolysis products typical of burning organic material.

Decomposition may produce styrene monomer and divinylbenzene.

## FIRE INCOMPATIBILITY

- Avoid contamination with oxidizing agents i.e. nitrates, oxidizing acids, chlorine bleaches, pool chlorine etc. as ignition may result.

## PERSONAL PROTECTION

- Glasses:  
Chemical goggles.
- Gloves:
- Respirator:  
Particulate

## Section 6 - ACCIDENTAL RELEASE MEASURES

### MINOR SPILLS

- Clean up all spills immediately.
- Avoid contact with skin and eyes.

### MAJOR SPILLS

- Clear area of personnel and move upwind.
- Alert Emergency Responders and tell them location and nature of hazard.

## Section 7 - HANDLING AND STORAGE

### PROCEDURE FOR HANDLING

- DO NOT pack ion-exchange columns with dried resin as the resin tends to expand when wetted and may cause the column to shatter.
- Limit all unnecessary personal contact.
- Wear protective clothing when risk of exposure occurs.

Empty containers may contain residual dust which has the potential to accumulate following settling. Such dusts may explode in the presence of an appropriate ignition source.

- Do NOT cut, drill, grind or weld such containers.
- In addition ensure such activity is not performed near full, partially empty or empty containers without appropriate workplace safety authorisation or permit.

Maximum operating temperature recommended is 75 deg C.

### RECOMMENDED STORAGE METHODS

- Lined metal can, Lined metal pail/drum
- Plastic pail.

### STORAGE REQUIREMENTS

- Store in original containers.
- Store at room temperature.
- Keep containers securely sealed.

## Section 8 - EXPOSURE CONTROLS / PERSONAL PROTECTION

### EXPOSURE CONTROLS

Source	Material	TWA ppm	TWA mg/m <sup>3</sup>	STEL ppm	STEL mg/m <sup>3</sup>	Peak ppm	Peak mg/m <sup>3</sup>	TWA F/CC	Notes
US - Oregon Permissible Exposure Limits (Z-3)	Amberlite IRA-900 Ion Exchange Resin (Inert or Nuisance Dust: (d) Total dust)		10						Oregon Permissible Exposure Limits (PELs) are different than the

			federal limits.
US OSHA Permissible Exposure Levels (PELs) - Table Z3	Amberlite IRA-900 Ion Exchange Resin (Inert or Nuisance Dust: (d) Respirable fraction)	5	
US OSHA Permissible Exposure Levels (PELs) - Table Z3	Amberlite IRA-900 Ion Exchange Resin (Inert or Nuisance Dust: (d) Total dust)	15	
US - Hawaii Air Contaminant Limits	Amberlite IRA-900 Ion Exchange Resin (Particulates not other wise regulated - Total dust)	10	
US - Hawaii Air Contaminant Limits	Amberlite IRA-900 Ion Exchange Resin (Particulates not other wise regulated - Respirable fraction)	5	
US - Oregon Permissible Exposure Limits (Z-3)	Amberlite IRA-900 Ion Exchange Resin (Inert or Nuisance Dust:(d) Respirable fraction)	5	Oregon Permissible Exposure Limits (PELs) are different than the federal limits.
Canada - Ontario Occupational Exposure Limits	Amberlite IRA-900 Ion Exchange Resin (Particles (Insoluble or Poorly Soluble) Not Otherwise)	10 (I)	
Canada - British Columbia Occupational Exposure Limits	Amberlite IRA-900 Ion Exchange Resin (Particles (Insoluble or Poorly Soluble) Not Otherwise Classified (PNOC))	10 (N)	
Canada - Ontario Occupational Exposure Limits	Amberlite IRA-900 Ion Exchange Resin (Specified (PNOS) / Particules (insolubles ou peu solubles) non précisées par ailleurs)	3 (R)	

US - Tennessee Occupational Exposure Limits - Limits For Air Contaminants	Amberlite IRA-900 Ion Exchange Resin (Particulates not otherwise regulated Respirable fraction)	5	
US - California Permissible Exposure Limits for Chemical Contaminants	Amberlite IRA-900 Ion Exchange Resin (Particulates not otherwise regulated Respirable fraction)	5	(n)
US - Oregon Permissible Exposure Limits (Z-1)	Amberlite IRA-900 Ion Exchange Resin (Particulates not otherwise regulated (PNOR) (f) Total Dust)	10	Bold print identifies substances for which the Oregon Permissible Exposure Limits (PELs) are different than the federal Limits. PNOR means "particles not otherwise regulated."
US - Michigan Exposure Limits for Air Contaminants	Amberlite IRA-900 Ion Exchange Resin (Particulates not otherwise regulated, Respirable dust)	5	
US - Oregon Permissible Exposure Limits (Z-1)	Amberlite IRA-900 Ion Exchange Resin (Particulates not otherwise regulated (PNOR) (f) Respirable Fraction)	5	Bold print identifies substances for which the Oregon Permissible Exposure Limits (PELs) are different than the federal Limits. PNOR means "particles not otherwise regulated."
US - Wyoming Toxic and Hazardous Substances Table Z1 Limits for Air Contaminants	Amberlite IRA-900 Ion Exchange Resin (Particulates not otherwise regulated (PNOR)(f)-Respirable fraction)	5	
Canada - Prince Edward Island Occupational Exposure Limits	Amberlite IRA-900 Ion Exchange Resin (Particles Insoluble or	10	See Appendix B current TLV/BEI Book

Poorly Soluble)  
[NOS] Inhalable  
particles)

ENDOELTABLE

### PERSONAL PROTECTION



### RESPIRATOR

•Particulate. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

### EYE

- Safety glasses with side shields
- Chemical goggles.

### HANDS/FEET

■ Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include: such as:

- frequency and duration of contact,
- chemical resistance of glove material,
- glove thickness and
- dexterity

Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent).

· When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.

· When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended.

· Contaminated gloves should be replaced.

Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended.

Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present.

- polychloroprene
- nitrile rubber
- butyl rubber
- fluorocautchouc
- polyvinyl chloride

Gloves should be examined for wear and/ or degradation constantly.

### OTHER

■ No special equipment needed when handling small quantities.

OTHERWISE:

- Overalls.
- Barrier cream.

### ENGINEERING CONTROLS

· Local exhaust ventilation is required where solids are handled as powders or crystals; even when particulates are relatively large, a certain proportion will be powdered by mutual friction.

· Exhaust ventilation should be designed to prevent accumulation and recirculation of particulates in the workplace.

## Section 9 - PHYSICAL AND CHEMICAL PROPERTIES

### PHYSICAL PROPERTIES

Solid.

Does not mix with water.

Sinks in water.

State	Divided solid	Molecular Weight	Not applicable
Melting Range (°F)	Not available	Viscosity	Not Applicable
Boiling Range (°F)	Not applicable	Solubility in water (g/L)	Immiscible
Flash Point (°F)	Not Available	pH (1% solution)	5-9 (slurry)
Decomposition Temp (°F)	>428	pH (as supplied)	Not applicable

Autoignition Temp (°F)	801	Vapor Pressure (mmHg)	16.951 @20C(H2O)
Upper Explosive Limit (%)	Not available	Specific Gravity (water=1)	1.1-1.4
Lower Explosive Limit (%)	Not available	Relative Vapor Density (air=1)	Not applicable
Volatile Component (%vol)	Negligible	Evaporation Rate	Not applicable

### APPEARANCE

Moist tan beads; do not mix with water.

## Section 10 - CHEMICAL STABILITY

### CONDITIONS CONTRIBUTING TO INSTABILITY

- Product is considered stable and hazardous polymerization will not occur.

### STORAGE INCOMPATIBILITY

- Avoid contamination of water, foodstuffs, feed or seed.

Avoid reaction with oxidizing agents.

Ion-exchange resins may react explosively with concentrated nitric acid solutions and with other strong oxidizing agents.

Forms explosive mixtures with oxidising acids.

For incompatible materials - refer to Section 7 - Handling and Storage.

## Section 11 - TOXICOLOGICAL INFORMATION

Amberlite IRA-900 Ion Exchange Resin

### TOXICITY AND IRRITATION

#### AMBERLITE IRA-900 ION EXCHANGE RESIN:

- No significant acute toxicological data identified in literature search.

## Section 12 - ECOLOGICAL INFORMATION

No data

### Ecotoxicity

Ingredient	Persistence: Water/Soil	Persistence: Air	Bioaccumulation	Mobility
Amberlite IRA-900 Exchange Resin	ion No Data Available	No Data Available		

## Section 13 - DISPOSAL CONSIDERATIONS

### Disposal Instructions

All waste must be handled in accordance with local, state and federal regulations.

‡ Legislation addressing waste disposal requirements may differ by country, state and/ or territory. Each user must refer to laws operating in their area. In some areas, certain wastes must be tracked.

A Hierarchy of Controls seems to be common - the user should investigate:

- Reduction
- Reuse
- Recycling
- Disposal (if all else fails)

This material may be recycled if unused, or if it has not been contaminated so as to make it unsuitable for its intended use. Shelf life considerations should also be applied in making decisions of this type. Note that properties of a material may change in use, and recycling or reuse may not always be appropriate.

DO NOT allow wash water from cleaning equipment to enter drains. Collect all wash water for treatment before disposal.

- Recycle wherever possible.
- Consult manufacturer for recycling options or consult Waste Management Authority for disposal if no suitable treatment or disposal facility can be identified.

## Section 14 - TRANSPORTATION INFORMATION



## Section 15 - REGULATORY INFORMATION

**Amberlite IRA-900 Ion Exchange Resin (CAS: 9050-97-9) is found on the following regulatory lists;**

"US - Hawaii Air Contaminant Limits", "US - Oregon Permissible Exposure Limits (Z-3)", "US OSHA Permissible Exposure Levels (PELs) - Table Z3"

## Section 16 - OTHER INFORMATION

*Reasonable care has been taken in the preparation of this information, but the author makes no warranty of merchantability or any other warranty, expressed or implied, with respect to this information. The author makes no representations and assumes no liability for any direct, incidental or consequential damages resulting from its use. For additional technical information please call our toxicology department on +800 CHEMCALL.*

■ Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

A list of reference resources used to assist the committee may be found at:  
[www.chemwatch.net/references](http://www.chemwatch.net/references).

■ The (M)SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered.

*This document is copyright. Apart from any fair dealing for the purposes of private study, research, review or criticism, as permitted under the Copyright Act, no part may be reproduced by any process without written permission from CHEMWATCH. TEL (+61 3) 9572 4700.*

Issue Date: Jul-24-2009

Print Date: Jul-15-2011